











Complete your **FORM...**

www.formsunger.com.tr

PRODUCT NAME	EUROPE STANDARDS			US STANDARDS	
	DENSITY	HARDNESS (NEWTON)	HARDNESS (KPA)	POUND (P)	ILD
	TS EN ISO 845	TS EN ISO 2439	TS EN ISO 3386 AVERAGE		
	KG/M3	N %40	KPA		
					
22 DN SOFT FORM	22	75	1,73	1,4	15
24 DN SOFT FORM	24	90	2,10	1,5	16
27 DN SOFT FORM	27	135	3,34	1,7	26
28 DN SOFT FORM	28	135	3,23	1,8	26
30 DN SOFT FORM	30	153	3,25	1,9	30
32 DN SOFT FORM	32	145	3,38	2,0	28
35 DN SOFT FORM	35	130	3,26	2,2	25
35 DN MAXSOFT FORM	35	103	2,22	2,2	20
					
24 DN HYPER SOFT FORM	24	55	1,21	1,5	11
35 DN HYPER SOFT FORM	35	85	2,16	2,2	16
					
14 DN FLEXI FORM	14	80	2,12	0,9	15
16 DN FLEXI FORM	16	95	2,21	1,0	18
18 DN FLEXI FORM	18	105	2,68	1,1	20
20 DN FLEXI FORM	20	115	2,69	1,3	22
22 DN FLEXI FORM	22	125	3,15	1,4	24
24 DN FLEXI FORM	24	135	3,13	1,5	26
26 DN FLEXI FORM	27	158	3,97	1,6	30
27 DN FLEXI FORM	27	160	3,90	1,8	0
28 DN FLEXI FORM	28	160	3,90	1,8	31
30 DN FLEXI FORM	30	176	3,95	1,9	34
32 DN FLEXI FORM	32	171	4,20	2,0	33
35 DN FLEXI FORM	35	181	4,25	2,2	35
40 DN FLEXI FORM	40	191	4,43	2,5	37
					
14 DN DURA FORM	14	106	2,51	0,9	20
14 DN MEGA DURA FORM	14	156	4,02	0,9	30
16 DN DURA FORM	16	105	2,82	1,0	20
16 DN MEGA DURA FORM	16	160	3,87	1,0	31
18 DN DURA FORM	18	130	3,60	1,1	25
18 DN MEGA DURA FORM	18	191	4,84	1,1	37
20 DN DURA FORM	20	176	4,60	1,3	34
22 DN DURA FORM	22	205	5,42	1,4	40
22 DN MEDIUM FORM	22	165	3,58	1,4	32
22 DN MEGA DURA FORM	22	247	6,40	1,4	48
24 DN DURA FORM	24	210	5,35	1,5	40
24 DN MEDIUM FORM	24	171	4,33	1,5	33
26 DN DURA FORM	26	229	5,68	1,6	44
32 DN DURA FORM	32	256	6,43	2,0	49

PRODUCT NAME	EUROPE STANDARDS			US STANDARDS	
	DENSITY	HARDNESS (NEWTON)	HARDNESS (KPA)	POUND (P)	ILD
	TS EN ISO 845	TS EN ISO 2439	TS EN ISO 3386 AVERAGE		
	KG/M3	N %40	KPA		
32 DN MEDIUM FORM	32	230	5,22	2,0	44
35 DN DURA FORM	35	245	5,85	2,2	47
40 DN DURA FORM	40	291	7,16	2,5	56
40 DN MEDIUM FORM	40	260	5,30	2,5	50
50 DN DURA FORM	50	460	12,90	3,1	89
60 DN DURA FORM	60	505	13,82	3,8	97
70 DN DURA FORM	70	663	16,21	4,4	32
					
30 DN HR FORM	30	130	3,26	1,9	25
35 DN HR FORM	35	145	3,65	2,2	28
35 DN SOFT HR FORM	35	105	2,46	2,2	20
40 DN HR FORM	40	140	3,44	2,5	27
50 DN HR FORM	50	160	3,83	3,1	31
50 DN SOFT HR FORM	50	130	3,08	3,1	25
					
32 DN PE VISCO FORM	32	65	1,62	2,0	13
40 DN PE VISCO FORM	40	70	1,92	2,5	14
45 DN VISCO FORM	45	60	1,32	2,8	12
50 DN PE VISCO FORM	50	76	1,81	3,1	15
50 DN VISCO FORM	50	60	1,81	3,1	12
60 DN PE VISCO FORM	60	60	1,66	3,8	12
60 DN VISCO FORM	60	70	1,86	3,8	14
					
32 DN PE VISCO GEL FORM	32	73	1,84	2,0	14
40 DN PE VISCO GEL FORM	40	75	1,86	2,5	12
50 DN VISCO GEL FORM	50	60	1,67	3,1	12
60 DN VISCO GEL FORM	60	70	1,71	3,8	14
					
14 DN FLARET FORM	14	67	1,91	0,9	13
18 DN FLARET FORM	18	76	1,76	1,1	15
20 DN FLARET FORM	20	85	4,55	1,3	16
22 DN FLARET FORM	22	127	3,09	1,4	25
22 DN SOFT FLARET FORM	22	75	1,72	1,4	15
24 DN FLARET FORM	24	115	3,20	1,5	22
24 DN CRIB5 FLARET FORM	24	95	2,32	1,5	18
26 DN FLARET FORM	26	181	4,22	1,6	35
27 DN FLARET FORM	27	130	2,97	1,7	25
28 DN FLARET FORM	28	186	3,24	1,8	36
28 DN CRIB5 FLARET FORM	28	125	3,15	1,8	24
28 DN SOFT FLARET FORM	28	135	3,08	1,8	26
32 DN DURA FLARET FORM	32	276	5,97	2,0	53

PRODUCT NAME	EUROPE STANDARDS			US STANDARDS	
	DENSITY	HARDNESS (NEWTON)	HARDNESS (KPA)	POUND (P)	ILD
	TS EN ISO 845	TS EN ISO 2439	TS EN ISO 3386 AVERAGE		
	KG/M3	N %40	KPA		
35 DN SOFT FLARET FORM	35	143	3,06	2,2	28
40 DN FLARET FORM	40	181	4,49	2,5	35
45 DN VISCO FLARET FORM	45	60	1,63	2,8	12
50 DN VISCO FLARET FORM	50	74	1,92	3,1	14



22 DN DURA OPTIC FORM	22	205	4,89	1,4	40
24 DN DURA OPTIC FORM	24	201	5,15	1,5	39
24 DN OPTIC FORM	24	125	2,97	1,5	24
24 DN SOFT OPTIC FORM	24	80	2,17	1,5	15
26 DN DURA OPTIC FORM	26	221	5,20	1,6	43
26 DN OPTIC FORM	26	130	3,14	1,6	25
30 DN DURA OPTIC FORM	30	221	5,39	1,9	43
30 DN OPTIC FORM	30	135	3,18	1,9	26
32 DN DURA OPTIC FORM	32	236	5,81	2,0	45
35 DN DURA OPTIC FORM	35	245	6,26	2,2	47
35 DN OPTIC FORM	35	160	3,83	2,2	31
35 DN SOFT OPTIC FORM	35	145	3,28	2,2	28
40 DN DURA OPTIC FORM	40	300	6,86	2,5	58
40 DN OPTIC FORM	40	171	4,27	2,5	33



16 DURA LAMINA PU FORM	16	124	2,77	1,0	24
22 DURA LAMINA PU FORM	20	178	4,64	1,3	34
22 DN LAMINA PU FORM	22	115	2,74	1,4	22
22 DN DURA LAMINA PU FORM	22	180	4,55	1,4	35
24 DN LAMINA PU FORM	24	135	3,30	1,5	26
24 DN SOFT LAMINA PU FORM	24	77	1,83	1,5	15
26 DN LAMINA PU FORM	26	135	3,21	1,6	26
32 DN LAMINA PU FORM	32	152	3,42	2,0	29